

Ecomass® 2150TU85

Polyamide 66

Ecomass Technologies

Message:

Ecomass®2150TU85 is a polyamide 66 (nylon 66) material that contains a tungsten filler. This product is available in North America and is processed by injection molding.

Ecomass®The main features of 2150TU85 are:

Good toughness

non-toxic

General Information			
Filler / Reinforcement	Tungsten packing		
Features	Good toughness		
	Non-toxic		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	5.60	g/cm ³	Internal method
Molding Shrinkage	0.90 - 1.0	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2
Tensile Stress (Yield)	43.0	MPa	ISO 527-2
Tensile Strain (Break)	9.0	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	6.0	kJ/m ²	ISO 180/A
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	79.4	°C	
Drying Time - Desiccant Dryer	2.0	hr	
Drying Time, Maximum	4.0	hr	
Processing (Melt) Temp	199 - 221	°C	
Mold Temperature	54.4 - 65.6	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.103 - 0.172	MPa	
Screw Speed	100 - 250	rpm	
Clamp Tonnage	3.4 - 5.5	kN/cm ²	
Cushion	6.35 - 12.7	mm	
Screw L/D Ratio	20.0:1.0		
Screw Compression Ratio	2.5:1.0		
Injection instructions			

Pack (Hold) Pressure: 65 to 75% of Injection Pressure Fill Time: 1.0 to 2.0 in/sec Pack (Hold) Time: 10 to 15 sec Cooling Time: As required Feed Throat:
Cooled Nozzle Type: Reverse Taper Check Type: Free Flow Dryer Dew Point: -20 to -40 °F Minimum Air Flow: 0.8 to 1.0 CFM Injection Pressure: As Required

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT