

# KRATON® D0243 K

Styrene Butadiene Block Copolymer

Kraton Polymers LLC

## Message:

Kraton D0243 K is a clear, diblock copolymer based on styrene and butadiene with a polystyrene content of 33%. It is supplied from North America in the physical form identified below.

Kraton D0243 KT - supplied as a porous pellet dusted with talc

Kraton D0243 K is used as a modifier of bitumen or thermoplastics and in compound formulations. It may also find use as an ingredient in formulating adhesives, sealants and coatings.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Block Copolymer		
Uses	Adhesives		
	Asphalt Modification		
	Coating Applications		
	Footwear		
	Plastics Modification		
	Sealants		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm <sup>3</sup>	ASTM D4025
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	20	g/10 min	ASTM D1238
Antioxidant Additive	0.35 to 0.48	%	Internal Method
Ash Content <sup>1</sup>	0.4 to 0.8	wt%	Internal Method
Extractables	< 1.0	%	Internal Method
Polystyrene Content	31 to 36	%	Internal Method
Solution Viscosity - Toluene, 25%wt (25°C)	170 to 430	mPa · s	Internal Method
Volatile Matter	< 1.0	%	Internal Method
Diblock Content	75.0		
Styrene/Rubber ratio	33/67		
Vinyl Polybutadiene Content	35	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	70		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	1.03	MPa	ASTM D412
Tensile Strength (Yield)	1.72	MPa	ASTM D412

## NOTE

1. Talc

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

