# Caltex PP H710

#### Polypropylene Homopolymer

#### **GS Caltex**

#### Message:

Caltex PP H710 is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Asia Pacific.

Important attributes of Caltex PP H710 are:

**High Stiffness** 

Homopolymer

Typical application of Caltex PP H710: Sheet

| General Information                     |                           |          |             |
|---|---------------------------|----------|-------------|
| Features                                | High Stiffness            |          |             |
|   | Homopolymer               |          |             |
|   |                           |          |             |
| Uses                                    | Blow Molding Applications |          |             |
|   | Sheet                     |          |             |
| Forms                                   | Pellets                   |          |             |
| Physical                                | Nominal Value             | Unit     | Test Method |
| Specific Gravity                        | 0.903                     | g/cm³    | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (230°C/2.16   |                           |          |             |
| kg)                                     | 0.70                      | g/10 min | ASTM D1238  |
| Molding Shrinkage                       |                           |          | ASTM D955   |
| Flow                                    | 1.5 to 1.9                | %        |             |
| Across Flow                             | 1.5 to 1.9                | %        |             |
| Hardness                                | Nominal Value             | Unit     | Test Method |
| Rockwell Hardness (R-Scale)             | 105                       |          | ASTM D785   |
| Mechanical                              | Nominal Value             | Unit     | Test Method |
| Tensile Strength (Yield)                | 37.3                      | MPa      | ASTM D638   |
| Tensile Elongation                      |                           |          | ASTM D638   |
| Yield                                   | 10                        | %        |             |
| Break                                   | > 500                     | %        |             |
| Flexural Modulus                        | 1570                      | MPa      | ASTM D790A  |
| Impact                                  | Nominal Value             | Unit     | Test Method |
| Notched Izod Impact                     | 37                        | J/m      | ASTM D256   |
| Thermal                                 | Nominal Value             | Unit     | Test Method |
| Deflection Temperature Under Load (0.45 | 125                       | °C       | ASTM D648   |
| MPa, Unannealed)                        |                           |          |             |
| Vicat Softening Temperature             | 152                       | °C       | ASTM D1525  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

