

Stat-Tech™ AS-15CF/000 BK001

Acrylonitrile Butadiene Styrene
PolyOne Corporation

Message:
15 % carbon fiber reinforced ABS compound

General Information			
Filler / Reinforcement	Carbon Fiber, 15% Filler by Weight		
Features	ESD Protection		
Uses	Aerospace Applications		
	Automotive Under the Hood		
	Business Equipment		
	Electrical/Electronic Applications		
	Housings		
	Printer Parts		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.15 to 0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	100	MPa	ASTM D638
Tensile Elongation ² (Break)	2.5 to 4.0	%	ASTM D638
Flexural Modulus	7600	MPa	ASTM D790
Flexural Strength	140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm, Injection Molded)	55	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	85.0	°C	
1.8 MPa, Unannealed, 3.18 mm	75.0	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+5	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 85.0	°C
Drying Time	4.0	hr
Processing (Melt) Temp	220 to 250	°C
Mold Temperature	65.0 to 85.0	°C
NOTE		
1.	Type I, 5.1 mm/min	
2.	Type I, 5.1 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT