

Tenac™-C ZLV40

Acetal (POM) Copolymer

Asahi Kasei Chemicals Corporation

Message:

Tenac™-C ZLV40 is an Acetal (POM) Copolymer product. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Tenac™-C ZLV40 include automotive, engineering/industrial parts and housings.

Characteristics include:

- Flame Rated
- Copolymer
- Lubricated
- Medium Viscosity
- Wear Resistant

General Information	
UL YellowCard	E48285-547658
Additive	Lubricant
Features	Copolymer
	Good Wear Resistance
	Low Friction
	Low VOC
	Lubricated
	Medium Viscosity
Uses	Automotive Applications
	Engineering Parts
	Gears
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.39	g/cm ³	ASTM D792
--	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (23°C, 24 hr, 50% RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	86		
R-Scale	117		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Stress			

Yield	61.0	MPa	ISO 527-2
--	56.0	MPa	ASTM D638
Tensile Elongation			
Break	25	%	ASTM D638
Break	20	%	ISO 527-2
Flexural Modulus	2600	MPa	ASTM D790, ISO 178
Flexural Strength	89.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179
Notched Izod Impact	56	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	157	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	100	°C	ASTM D648, ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696, ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (0.790 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

