

Next Nylon 66 Prime Series PG40-01BK

Polyamide 66

Next Polymers Ltd.

Message:

Description

PA66 Glass Fiber Reinforced Black Compound

Product Applications

This grade is widely used for Automotive parts - pedal oil filter housing, clutch master cylinder etc

Benefits

offering Excellent combination of thermal stability and Mechanical properties

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight			
Features	Thermal stability, good			
Uses	Application in Automobile Field			
Agency Ratings	EC 1907/2006 (REACH)			
RoHS Compliance	RoHS compliance			
Appearance	Black			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.46	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.20	--	%	ASTM D955
Transverse flow	0.45	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	1.7	--	%	ASTM D570
Saturation ¹	5.8	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
Class m	105	--		ASTM D785
Class r	125	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	200	160	MPa	ASTM D638
Tensile Elongation (Break)	4.0	6.0	%	ASTM D638
Flexural Modulus	11000	6500	MPa	ASTM D790
Flexural Strength	285	220	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	160	190	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648

0.45 MPa, not annealed	260	--	°C	ASTM D648
1.8 MPa, not annealed	254	--	°C	ASTM D648
Melting Temperature	262	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+16	--	ohms	IEC 60093
Volume Resistivity	1.0E+14	--	ohms·cm	IEC 60093
Dielectric Strength	27	24	kV/mm	IEC 60243-1
Comparative Tracking Index	> 600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94

Additional Information

干燥

This grade is not suitable for food contact, medical devices or toy applications

Injection	Dry	Unit	
Drying Temperature - Hot Air Dryer	80.0	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	270 - 280	°C	
Middle Temperature	280 - 290	°C	
Front Temperature	290 - 300	°C	
Mold Temperature	65.0 - 85.0	°C	

NOTE

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT