

Siveras™ L304T35H

Liquid Crystal Polymer

Toray Resin Company

Message:

Siveras™ L304T35H is a Liquid Crystal Polymer (LCP) product filled with 35% glass\mineral. It is available in Asia Pacific, Europe, or North America. Characteristics include:
Flame Rated
Warp Resistant

General Information			
Filler / Reinforcement	Glass\Mineral,35% Filler by Weight		
Features	Low Warpage		
Part Marking Code	>LCP-(GF+MD)35<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm ³	ASTM D792
Molding Shrinkage			Internal Method
Across Flow : 1.00 mm ¹	0.61	%	
Flow : 1.00 mm ²	0.020	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	120	MPa	ASTM D638
Tensile Elongation (Break)	3.1	%	ASTM D638
Flexural Modulus	11200	MPa	ASTM D790
Flexural Strength	145	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	ASTM D648
CLTE - Flow	1.3E-5 to 1.9E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (0.380 mm)	V-0		UL 94
NOTE			
1.	80x80x1		
2.	80x80x1mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

