

KumhoSunny ABS HAG5210FR

Acrylonitrile Butadiene Styrene

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HAG5210FR is 10%GF and V0 enviromental ABS resin.It has balance flow properties,mechanical properties and a wide processing window.HAG5210FR is mainly used in electric & electron parts, air-condition fan, office equipments requiring flame class,etc.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Flame Retardant		
Uses	Business Equipment		
	Electrical/Electronic Applications		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	60.0	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	3500	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	90.0	°C	ASTM D648
Vicat Softening Temperature	103	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		

Additional Information	Nominal Value	
CSA File No.	LS 66457	
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	2.0 to 3.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	210 to 220	°C
Middle Temperature	220 to 230	°C
Front Temperature	220 to 240	°C
Nozzle Temperature	220 to 240	°C
Processing (Melt) Temp	210 to 230	°C
Mold Temperature	40.0 to 80.0	°C
Back Pressure	1.00 to 5.00	MPa
Screw Speed	30 to 60	rpm
NOTE		
1.	Rate B (120°C/h)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

