## Verolloy A2703

Acrylonitrile Butadiene Styrene + Nylon

PlastxWorld Inc.

## Message:

Verolloy A2703 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) product filled with 15% glass fiber. It is available in Europe or North America. Characteristics include:

Flame Rated

**Heat Resistant** 

High Strength

Impact Resistant

Flame Rating (1.50 mm)

ΗВ

General Information				
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Features		High Heat Resistance		
		High Impact Resistance		
		High Tensile Strength		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.18		g/cm³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50		%	ASTM D955
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness	118			ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Break)	89.6	68.9	MPa	ASTM D638
Tensile Elongation (Break)	5.0	5.0	%	ASTM D638
Flexural Modulus	4140	3450	MPa	ASTM D790
Flexural Strength	145	110	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
		150	J/m	
23°C, 3.18 mm	120		J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa,				
Unannealed)	180	170	°C	ASTM D648
Flammability	Dry	Conditioned		Test Method
				•

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

UL 94

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

