

# EL-Lene™ H1000PYL

High Density Polyethylene

SCG Chemicals Co., Ltd.

## Message:

EL-Lene H1000PYL is a yellow, bimodal technology, high density polyethylene compound that is specially designed for striping. EL-Lene H1000PYL consists of high UV stabilizer and anti-oxidant which are well dispersed and provides outstanding UVresistance and high thermal stability for long term using.

General Information			
Additive	Antioxidant UV Stabilizer		
Features	Antioxidant Good Processability Good Thermal Stability Good UV Resistance High Strength		
Uses	Piping		
Appearance	Yellow		
Forms	Pellets		
Processing Method	Extrusion Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.951	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.28	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (F0)	> 10000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	66		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/100
Yield	23.0	MPa	
Break	36.0	MPa	
Tensile Strain (Break)	850	%	ISO 527-2/100
Flexural Modulus	1000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	200	J/m	
0°C	260	J/m	

23°C	300	J/m	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	ASTM D746
Vicat Softening Temperature	122	°C	ASTM D1525
Oxidation Induction Time (200°C)	> 50	min	ISO 10837
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

