

# PLEXIGLAS® Sheet Soundstop XT

Polymethyl Methacrylate Acrylic

Evonik Industries AG

## Message:

PLEXIGLAS® Soundstop XT is a highly transparent grade of extruded acrylic. Applications: These properties make PLEXIGLAS® Soundstop XT especially suitable for - noise control along roads and railways  
wind barriers on bridges

General Information			
Features	Good Impact Resistance		
	Good Weather Resistance		
	High Hardness		
	Recyclable Material		
Appearance	Clear/Transparent		
Forms	Sheet		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2/1B/5
Tensile Stress <sup>1</sup>	70.0	MPa	ISO 527-2/5
Tensile Strain (Break)	4.0	%	ISO 527-2/1B/5
Flexural Stress	98.0	MPa	ISO 178
Poisson's Ratio	0.37		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	102	°C	ISO 306/B
CLTE - Flow (0 to 50°C)	7.0E-5	cm/cm/°C	DIN 53752-A
Maximum Service Temperature	70	°C	
Light Transmission - of clear- transparent elements	> 92	%	DIN 5036
Weight per Unit Area (1.50 cm)	17.8	kg/m <sup>2</sup>	
	33 dB at 25 mm		
	32 dB at 20 mm		
Weighted Sound Reduction Index	30 dB at 15 mm		EN 1793-2
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

