Yuyao PC PC101

Polycarbonate

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PC PC101 is a Polycarbonate (PC) product. It can be processed by injection molding and is available in Asia Pacific. Typical application: Electrical/Electronic Applications.

Characteristics include:

Flame Rated

Flame Retardant

Good Toughness

Heat Resistant

High Gloss

| General Information | | | |
|---|-------------------------|---------|-------------|
| Additive | Flame Retardant | | |
| Features | Electrically Insulating | | |
| | Flame Retardant | | |
| | Good Stability | | |
| | Good Toughness | | |
| | High Gloss | | |
| | High Heat Resistance | | |
| Uses | Electrical Parts | | |
| Appearance | White | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.10 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.20 to 0.30 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 95.0 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 6.0 | % | ASTM D638 |
| Flexural Modulus | 4000 | MPa | ASTM D790 |
| Flexural Strength | 110 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (Area) | 13.0 | kJ/m² | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 150 | °C | ASTM D648 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 4.0E+16 | ohms·cm | ASTM D257 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating | | | UL 94 |
| 1.60 mm | V-1 | | |

| 3.20 mm | V-0 | | |
|------------------------|---------------|------|--|
| Injection | Nominal Value | Unit | |
| Drying Temperature | 105 to 110 | °C | |
| Drying Time | 4.0 to 5.0 | hr | |
| Processing (Melt) Temp | 210 to 255 | °C | |
| Mold Temperature | 60.0 to 80.0 | °C | |
| Injection Pressure | 70.0 to 100 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

