

TAROPRENE® 2 A50 E1G

Thermoplastic Vulcanizate

Taro Plast S.p.A.

Message:

Thermoplastic Elastomer Vulcanized. This TPE-V compound combines the typical performance of a vulcanized elastomer with the easy processing of a thermoplastic compound. Taroprene is totally recyclable and it can be produced in standard grades and in tailor-made grades.

General Information			
Features	Good Processability		
	Recyclable Material		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	4.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	50		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ASTM D412
100% Strain	1.65	MPa	
300% Strain	2.70	MPa	
Tensile Strength ² (Break)	4.30	MPa	ASTM D412
Tensile Elongation ³ (Break)	610	%	ASTM D412
Tear Strength	22.9	kN/m	ASTM D624
Compression Set			ASTM D395B
70°C, 22 hr	32	%	
100°C, 22 hr	38	%	
Extrusion	Nominal Value	Unit	
Melt Temperature	150 to 230	°C	
NOTE			
1.	Die C		
2.	Die C		
3.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

