Shin-Etsu Elastomer SV-17500U

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

SV-17500U is one of a series of easy processing, silicone rubber bases. It can be used in a variety of applications requiring finishing by molding, extruding or calendaring.

This product can be blended with other Shin-Etsu general purpose or no post cure bases for intermediate properties. The choice between these bases will depend on specific requirements.

Typical Applications Roll covers. Diaphragms.

| General Information | | |
|--------------------------------|-------------------|-------|
| Features | Workability, good | |
| | General | |
| | | |
| Uses | Diaphragm | |
| | General | |
| | | |
| Processing Method | Extrusion | |
| | Calendering | |
| | Injection molding | |
| | | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.23 | g/cm³ |
| Hardness | Nominal Value | Unit |
| Durometer Hardness | 75 | |
| Elastomers | Nominal Value | Unit |
| Tensile Stress (100% Strain) | 2.93 | MPa |
| Tensile Strength | 9.93 | MPa |
| Tensile Elongation (Break) | 330 | % |
| Tear Strength ¹ | 21.5 | kN/m |
| Compression Set (177°C, 22 hr) | 22 | % |
| Thermoset | Nominal Value | Unit |
| Post Cure Time (200°C) | 4.0 | hr |
| Additional Information | Nominal Value | Unit |
| Cure Agent | DBPH | |
| Press / Post Cure: Press | | |
| Uncured Properties | Nominal Value | Unit |
| Curing Time | 0.17 | hr |
| NOTE | | |
| 1. | B mould | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

