Okirol® E-6F

Expanded Polystyrene

DIOKI d.d.

Message:

Okirol[®] E-6F is expandable flame retardant polystyrene containing, apart from flame retardant agent, also pentane as the blowing agent. The product is supplied as spherical beads.

Okirol® E-6F is used for the manufacture of medium and high density blocks, panels with good mechanical properties intended for thermal insulation in construction industry, and industrial packaging.

Products made of Okirol® E-6F have fire characteristics in accordance with DIN 4102-1, class B1

| General Information | | | |
|---------------------|-----------------------------------|-------|--------------|
| Additive | Blowing Agent | | |
| | Flame Retardant | | |
| Features | Flame Retardant | | |
| Uses | Construction Applications | | |
| | Insulation | | |
| | Packaging | | |
| | Reinforced Panels | | |
| | | | |
| Agency Ratings | DIN 4102/B1 | | |
| | EC 1907/2006 (REACH) | | |
| | EU 94/62/EC | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Forms | Spheres | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | | | |
| 1 | 0.0180 | g/cm³ | |
| ² | 0.0190 to 0.0300 | g/cm³ | EN 1602 |
| Apparent Density | 0.62 | g/cm³ | ISO 60 |
| Flammability | Nominal Value | | Test Method |
| Reaction to Fire | Class E | | ISO 11925-2 |
| Bead Size | | | ISO 2591-1 |
| | 500.0 to 700.0 | μm | |
| Range ³ | 400.0 to 800.0 | μm | |
| Blowing Agent | 5.0 to 6.5 | % | ASTM 7132-05 |
| NOTE | | | |
| 1. | Minimum density of expanded beads | | |
| 2. | Density of molded product | | |
| 3. | >95% | | |
| | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

