

Globalprene® 3412P

Styrene Butadiene Styrene Block Copolymer

Lee Chang Yung Chemical Industry Corp.

Message:

- Property
- radial block copolymer
- high strength and low viscosity
- high tensile strength
- Application
- modifier for asphalt mixtures
- plastics modification
- shoe sole modification

General Information			
Features	Block Copolymer		
	Branched Polymer Structure		
	High Strength		
	High Tensile Strength		
	Low Viscosity		
Uses	Asphalt Modification		
	Footwear		
	Plastics Modification		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm ³	ASTM D792
Ash Content	< 7.0	%	ASTM D1416
Block Styrene	33	%	ASTM D3314
Volatile Matter	< 1.0	%	ASTM D1416
Brookfield Viscosity	20.0	Pa·s	ASTM D1084
BD/SM Ratio	67/33 %		ASTM D1416
Diblock Content	15	%	ASTM D5296
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	2.94	MPa	ASTM D412
Tensile Strength	19.6	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT