ALFATER XL® D50E 2GP0000

Thermoplastic Vulcanizate

ALBIS PLASTIC GmbH

Message:

ALFATER XL® D50E 2GP0000 is a Thermoplastic Vulcanizate (TPV) product. It can be processed by blow molding or extrusion and is available in Asia Pacific, Europe, or North America. Applications of ALFATER XL® D50E 2GP0000 include automotive, construction applications, electrical/electronic applications, sealing applications and wire & cable.

Characteristics include:

REACH Compliant

RoHS Compliant

Good Weather Resistance

General Information

| Features | Alkali Resistant | | | |
|---|------------------------------------|-------|-------------|--|
| | Good Weather Resistance | | | |
| | Ozone Resistant | | | |
| | | | | |
| Uses | Automotive Applications | | | |
| | Blow Molding Applications | | | |
| | Cable Jacketing | | | |
| | Construction Applications | | | |
| | Electrical/Electronic Applications | | | |
| | Profiles | | | |
| | Seals | | | |
| | | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | | |
| RoHS Compliance | RoHS Compliant | | | |
| Processing Method | Blow Molding | | | |
| | Extrusion | | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 0.950 | g/cm³ | ISO 1183 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Shore Hardness (Shore D) | 50 | | ISO 868 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Stress (100% Strain) | 13.5 | MPa | ISO 527-2 | |
| Elastomers | Nominal Value | Unit | Test Method | |
| Tensile Stress (Yield) | 28.0 | МРа | ISO 37 | |
| Tensile Elongation (Break) | 750 | % | ISO 37 | |
| Tear Strength | 100 | kN/m | ISO 34-1 | |
| Compression Set ¹ (100°C, 22 hr) | 80 | % | ISO 815 | |
| Thermal | Nominal Value | Unit | | |

| Service Temperature | -40 to 125 | °C | |
|---------------------|---------------|------|--|
| Injection | Nominal Value | Unit | |
| Drying Temperature | 70.0 to 80.0 | °C | |
| Drying Time | 2.0 to 4.0 | hr | |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 195 to 215 | °C | |
| NOTE | | | |
| 1. | 25% | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

