

ESENTTIA 20H10NA

Polypropylene Homopolymer

Polipropileno del Caribe S.A.

Message:

Characteristics: Control reology high melt flow rate Homopolymer polypropylene, easy mold filling, good stiffness/impact balance,, with nucleant and antistatic additives.
Recommended for: Injection molding of thin wall rigid containers, fast cycle time, cover electrical appliances, closures, general purpose injection molding applications.

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Controlled Rheology		
	Fast Molding Cycle		
	Food Contact Acceptable		
	General Purpose		
	High Flow		
	High Rigidity		
	Homopolymer		
	Nucleated		
Uses	Appliances		
	Closures		
	General Purpose		
	Thin-walled Containers		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EC 2023/2006		
	EU 10/2011		
	FDA 21 CFR 177.1520(a)(3)(i)(c)(1)		
	FDA 21 CFR 177.1520(b)		
	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	22	g/10 min	ASTM D1238

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, 3.20 mm, Injection Molded)	35.9	MPa	ASTM D638
Tensile Elongation ³ (Yield, 3.20 mm, Injection Molded)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ⁴ (3.20 mm, Injection Molded)	1590	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	37	J/m	ASTM D256A
NOTE			
1.	Procedure B		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

