

# Telcar® TL-1431H

Thermoplastic Elastomer

Teknor Apex Company

## Message:

Telcar® TL-1431H is a general purpose thermoplastic elastomer designed for automotive applications. Telcar® TL-1431H is a medium hardness grade suitable for injection molding and extrusion.

General Information	
Features	Low liquidity
	Fill
	Medium density
	Medium hardness
Uses	Wheels
	Industrial application
	General
	Consumer goods application field
RoHS Compliance	RoHS compliance
Appearance	Natural color
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.40	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 second, injection molding	70		ASTM D2240
Shore A, 5 seconds, injection molding	68		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup>			ASTM D412
Transverse flow: 100% strain	2.61	MPa	ASTM D412
Flow: 100% strain	3.71	MPa	ASTM D412
Transverse flow: 300% strain	4.19	MPa	ASTM D412
Flow: 300% strain	5.36	MPa	ASTM D412
Tensile Strength <sup>2</sup>			ASTM D412
Transverse flow: Fracture	9.83	MPa	ASTM D412
Flow: Fracture	8.23	MPa	ASTM D412

Tensile Elongation <sup>3</sup>			ASTM D412
Transverse flow: Fracture	660	%	ASTM D412
Flow: Fracture	570	%	ASTM D412
Tear Strength <sup>4</sup>			ASTM D624
Transverse flow	39.6	kN/m	ASTM D624
Flow	35.2	kN/m	ASTM D624
Compression Set <sup>5</sup>			ASTM D395B
23°C, 22 hr	21	%	ASTM D395B
70°C, 22 hr	83	%	ASTM D395B

#### Legal statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Rear Temperature	171 - 193	°C
Middle Temperature	177 - 199	°C
Front Temperature	182 - 204	°C
Nozzle Temperature	188 - 210	°C
Processing (Melt) Temp	188 - 210	°C
Mold Temperature	25 - 66	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.172 - 0.345	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

#### Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	166 - 188	°C
Cylinder Zone 2 Temp.	171 - 193	°C
Cylinder Zone 3 Temp.	177 - 199	°C
Cylinder Zone 4 Temp.	177 - 199	°C
Cylinder Zone 5 Temp.	182 - 204	°C
Die Temperature	190 - 210	°C

#### Extrusion instructions

Screw Speed: 30 to 100 rpm

#### NOTE

1. C mold, 510mm/min
2. C mold, 510mm/min

3.	C mold, 510mm/min
4.	C mold, 510mm/min
5.	Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

