

# Syncure™ S1044B Black

Crosslinked Polyethylene

PolyOne Corporation

## Message:

It can be used as a catalyst masterbatch component for the Pulitzer Syncure system.

General Information			
Uses	Wire and cable applications		
Appearance	Black		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ASTM D1505
Apparent Density <sup>1</sup>	0.60	g/cm <sup>3</sup>	Internal method
Melt Mass-Flow Rate (MFR) <sup>2</sup> (190°C/2.16 kg)	0.49	g/10 min	ASTM D1238
Additional Information			
凝胶值大于70,基于90 phr S1054A / 10 phr S1044B Syncure系统测量得出;并在蒸汽中硫化8小时.颗粒外观为1/8" 黑色珠子.			
NOTE			
1.	Geon® 1169		
2.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT