

Tectron H2337

Thermoplastic Vulcanizate

TECTRON Systems Pte Ltd

Message:

A thermoplastic vulcanizate with excellent heat and low temperature resistance. It can withstand temperature ranging from -50°C to 135°C. Tectron H series are available in concentrate and compound with hardness ranging from 45A - 90A. The concentrate is designed for compounders to obtain TPVs with the addition of PP and other chemicals. It can also be used as an additive to enhance the overall properties of various polymers. It can be processed by conventional plastics machines i.e. injection molding and extrusion.

| General Information | | | |
|------------------------------|-----------------------|-------------------|-------------|
| Features | Good wear resistance | | |
| | Heat resistance, high | | |
| Forms | Particle | | |
| Processing Method | Extrusion | | |
| | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.940 | g/cm ³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 70 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 2.70 | MPa | ASTM D412 |
| Tensile Strength (Yield) | 6.60 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 900 | % | ASTM D412 |
| Compression Set | | | ASTM D395 |
| 25°C, 22 hr | 13 | % | ASTM D395 |
| 100°C, 22 hr | 69 | % | ASTM D395 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 70.0 | °C | |
| Drying Time | 2.0 - 4.0 | hr | |
| Rear Temperature | 130 - 140 | °C | |
| Middle Temperature | 150 - 160 | °C | |
| Front Temperature | 160 - 170 | °C | |
| Nozzle Temperature | 180 - 200 | °C | |
| Mold Temperature | 30.0 - 40.0 | °C | |
| Back Pressure | 0.00 - 0.0800 | MPa | |
| Screw Speed | 35 - 110 | rpm | |
| Injection instructions | | | |

Injection Speed: 20 to 80 mm/s1st Stage - Boost Pressure: 1350 to 6000Hold Time (thick part): 2 to 15 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

