

Weihai Hisea CPE135A

Chlorinated Polyethylene

Weihai Hisea Plastic Rubber Co., LTD.

Message:

The product is no rules structure of the saturated thermoplastic resin, its appearance is white powder; it can be mixed and used with PVC, evidently increasing the impact resistance strength in lower temperature, flame resistance, ageing resistance and flexure performance. CPE135A mainly used in products such as window profiles, pipes, pipefittings, extrusion board, and also used in magnetic materials, such as magnetic rubber strips and all type of flattened magnet.

General Information		
Uses	Piping system	
	Doors and Windows	
	Accessories	
	Plastic modification	
	Profile	
Appearance	White	
Forms	Powder	
Physical	Nominal Value	Unit
Chlorine Content	34.0 - 36.0	wt%
Sieve Analysis - 0.9 mm Mesh		%
Volatile Matter		%
Heat of Fusion		J/g
Impurities		pcs/100 g
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	< 60	
Mechanical	Nominal Value	Unit
Tensile Strength	> 8.00	MPa
Tensile Elongation (Break)	> 700	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT