

RTP 2700 S-50A FR

Styrene Ethylene Butylene Styrene Block Copolymer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
Non-PBDE/PBB

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8 to 2.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	50		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7.58	MPa	ASTM D412
Tensile Elongation (Yield)	> 1000	%	ASTM D412
Tear Strength ¹	35.0	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	No Break		ASTM D256
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D4812
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Values per RTP Company testing.)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	182 to 232	°C	
Mold Temperature	15.6 to 37.8	°C	
Injection Pressure	68.9 to 103	MPa	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

