

Bergadur™ PB40 G15 H Natural

Polybutylene Terephthalate

PolyOne Corporation

Message:

Bergadur™PB40 G15 H Natural is a polybutene terephthalate (PBT) product, which contains a 15% glass fiber reinforced material. It can be processed by injection molding and is available in Europe.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Thermal Stability		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5400	MPa	ISO 527-2
Tensile Stress	100	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.1	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	28	kJ/m ²	ISO 179
Injection	Nominal Value	Unit	
Drying Temperature	110 - 130	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	240 - 270	°C	
Middle Temperature	240 - 270	°C	
Front Temperature	240 - 270	°C	
Mold Temperature	75 - 95	°C	
Injection instructions			

Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT