RTP 2209 HF UP

Polyetheretherketone

RTP Company

Message:

"Warning: The status of this material is 'Commercial: Limited Issue'

The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade."

| General Information | | | |
|--|---|-----------------------------------|-------------|
| Filler / Reinforcement | Glass fiber reinforced material, 50% filler by weight | | |
| Features | High liquidity | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.73 | g/cm³ | ISO 1183 |
| Moisture Content | 0.10 | % | |
| Primary Additive | 50 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus (Injection Molded) | 19500 | MPa | ISO 527-2 |
| Tensile Stress | 240 | MPa | ISO 527-2 |
| Tensile Strain (Yield, Injection Molded) | 2.0 | % | ISO 527-2 |
| Flexural Modulus (Injection Molded) | 17000 | MPa | ISO 178 |
| Flexural Stress (Injection Molded) | 355 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact ¹ (Injection Molded) | 12 | kJ/m² | ISO 180/1A |
| Unnotched Izod Impact Strength ² (Injection Molded) | 65 | kJ/m² | ISO 180/1U |
| Additional Information | Nominal Value | Unit | |
| Data listed is for natural or black colored ma | aterials. Pigments can affect pr | operties.Desiccant Type Dryer Red | quired. |
| Injection | Nominal Value | Unit | |
| Drying Temperature - Desiccant Dryer | 150 | °C | |
| Drying Time - Desiccant Dryer | 3.0 | hr | |
| Dew Point | -30.0 | °C | |
| Processing (Melt) Temp | 350 - 400 | °C | |
| Mold Temperature | 160 - 220 | °C | |
| Injection Pressure | 80.0 - 125 | MPa | |
| NOTE | | | |
| 1. | 4mm thickness | | |
| 2. | 4mm thickness | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

