Geon[™] Vinyl Flexible A87UB

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon[™]Vinyl Flexible A87UB is a flexible polyvinyl chloride product. It can be processed by extrusion or injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Geon[™]Vinyl Flexible A87UB's application fields include hoses and construction applications. The main characteristics are: UV stability.

General Information			
Additive	Insecticide		
	UV stabilizer		
Features	UV absorption		
Uses	Floor Material		
	Pipe		
	Pipe fittings		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	91		ASTM D2240
Shaw A, 15 seconds	83		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Fracture	17.2	MPa	ASTM D638
100% strain	10.3	MPa	ASTM D638
Tensile Elongation ² (Break)	320	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	87.6	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-39.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	24	%	ASTM D2863
Injection	Nominal Value	Unit	
Processing (Melt) Temp	193 - 204	°C	

Extrusion	Nominal Value	Unit
Melt Temperature	174 - 179	°C
NOTE		
1.	510 mm/min	
2.	510 mm/min	
3.	C mold, 510mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

