

SAXATEC™ 4210

Acrylonitrile Styrene Acrylate
SAX Polymers

Message:

SAXATEC 4210 is a high heat resistant, high viscosity and weatherable ASA injection molding grade, characterized by high impact strength and high stiffness.

General Information			
Features	Good Weather Resistance		
	Heat Stabilized		
	High Heat Resistance		
	High Impact Resistance		
	High Stiffness		
	High Viscosity		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	10.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Moisture Content ¹	< 0.20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2800	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	58.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	20	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.0	kJ/m ²	
23°C	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	60	kJ/m ²	
23°C	100	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m ²	
23°C	8.0	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180
-30°C	40	kJ/m ²	
23°C	80	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature ² (1.8 MPa, Unannealed, 60.0 mm Span)	96.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B50
Ball Pressure Test (95°C, 2.00 mm)	Pass		IEC 60335-1
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	B130		
2.	80*10*4mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT