

# PrimoPrene 60A-4000

Thermoplastic Vulcanizate Alloy

KMI Group Inc.

Message:

Attributes:

PrimoPrene is a thermoplastic vulcanizate containing EPDM and PP.  
It is designed for applications requiring long term sealing performance even at elevated temperatures up to 135°C (275F).  
Soft-touch feel for grips and handles used in automotive and consumer goods.  
Can be processed using conventional thermoplastic processing equipment.  
PrimoPrene 4000 series are naturally colorless: making them ideal for vibrant color applications.  
Suitable for injection molding, profile extrusion and sheet applications.  
PrimoPrene 60A-4000 is UV stabilized: meeting the most stringent automotive requirements.

Applications:

PrimoPrene is a cost effective solution for replacing Santoprene rubber, styrenic-based TPEs, flexible PVC, and thermoset rubbers such as EPDM, and Polychloroprene. It is an excellent choice for applications requiring flexibility in the following markets: automotive parts, appliance, business machines, construction, consumer products, and electronics.

General Information			
Filler / Reinforcement		Polypropylene	
Additive		Rubber	
		UV Stabilizer	
Features		Good Colorability	
		Good Flexibility	
		Good Heat Seal	
		Good UV Resistance	
		Soft	
Uses		Appliances	
		Automotive Applications	
		Business Equipment	
		Construction Applications	
		Consumer Applications	
		Electrical/Electronic Applications	
		Flexible Grips	
		Handles	
Appearance		Colorless	
Processing Method		Extrusion	
		Injection Molding	
		Profile Extrusion	
		Sheet Extrusion	
Physical	Nominal Value	Unit	Test Method

Specific Gravity	0.940	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec	60		
Shore A, 15 sec	57		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (100% Strain, 23°C)	2.20	MPa	ASTM D412
Tensile Strength <sup>2</sup> (Yield, 23°C)	4.30	MPa	ASTM D412
Tensile Elongation <sup>3</sup> (Break, 23°C)	480	%	ASTM D412
Tear Strength <sup>4</sup> (23°C)	28.0	kN/m	ASTM D624
Compression Set			ASTM D395
70°C, 22 hr	24	%	
125°C, 70 hr	46	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Melting Temperature	159	°C	
Additional Information	Nominal Value		Test Method
Ozone Resistance <sup>5</sup>	Excellent		ASTM D1149
NOTE			
1.	500 mm/min		
2.	500 mm/min		
3.	500 mm/min		
4.	Die C, 500 mm/min		
5.	500 hr, 100 pphm O3 conc.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT