

OP - PPS 30GF-15PTFE

Polyphenylene Sulfide

Oxford Polymers

Message:

OP - PPS 30GF-15PTFE is a Polyphenylene Sulfide (PPS) material filled with 30% glass fiber and 15% ptfe fiber. It is available in North America for injection molding. Primary attribute of OP - PPS 30GF-15PTFE: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
	PTFE Fiber,15% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.66	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	131	MPa	
Break	131	MPa	
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength	162	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (4°C)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	266	°C	
1.8 MPa, Unannealed, 3.18 mm	260	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	V-0		
3.18 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	93.3 to 121	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	288 to 316	°C	
Middle Temperature	288 to 307	°C	
Front Temperature	288 to 307	°C	
Processing (Melt) Temp	293 to 321	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

