## Propafilm™ SRC110

Polypropylene Alloy Innovia Films Ltd.

## Message:

Shrink Tightening Acrylic Coated Film

Biaxially oriented polypropylene (BOPP) film coated on both sides with an aqueous acrylic (chlorine free) dispersion.

SRC95/110 are suitable for use as a carton, naked collation or bundle overwrap in the tobacco or other packaging industries where exceptional appearance, aroma barrier and wrap tightness are required.

General Information				
Features	Excellent Printability			
	Food Contact Acceptable			
	Low Moisture Vapor Transmission			
	20W Moistare Vapor Harismissie	· · ·		
Uses	Bi-axially Oriented Film			
	Packaging			
Agency Ratings	FDA 21 CFR 177.1520			
Forms	Film			
Physical	Nominal Value	Unit	Test Method	
Molding Shrinkage			Internal Method	
Flow: 80°C, 1 min	1.5	%		
Flow: 120°C, 1 min	6.0	%		
Across Flow: 80°C, 1 min	1.0	%		
Across Flow: 120°C, 1 min	9.0	%		
Mechanical	Nominal Value	Unit	Test Method	
Coefficient of Friction			ASTM D1894	
vs. Itself - Dynamic, Outside/Outside	0.20 to 0.30			
vs. Itself - Static, Outside/Outside	0.20 to 0.30			
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	2800	μm		
Seal Strength <sup>1</sup>	0.15	N/mm	Internal Method	
Seal Initiation Temperature <sup>2</sup>	85.0 to 143	°C	Internal Method	
Oxygen Permeability			ASTM F1927	
23°C, 85% RH	19	cm³·mm/m²/atm/24 hr	cm³·mm/m²/atm/24 hr	
25°C, 0% RH	22	cm³·mm/m²/atm/24 hr		
Water Vapor Transmission Rate			ASTM F1770	
23°C, 85% RH	0.93	g/m²/24 hr		
38°C, 90% RH	5.4	g/m²/24 hr		
Yield	40.3	m²/kg	Internal Method	
Optical	Nominal Value	Unit	Test Method	

Gloss (45°)	90		ASTM D2457	
Haze <sup>3</sup>	2.0 to 2.5	%	ASTM D1003	
NOTE				
1.	266°F; 1sec; 15lb/in²	266°F; 1sec; 15lb/in²		
2.	2secs; 15psi	2secs; 15psi		
3.	Wide angle; 2.5°			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

