

# AURAPENE PPTF40 Black

Compounded Polypropylene  
Aurora Manufacturing Ltd

Message:

PPTF40BK is a general purpose 40% talc filled polypropylene compound with good UV performance, manufactured from recycled polymer.

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Recycled Content	Yes		
Features	General Purpose		
	Good UV Resistance		
Uses	General Purpose		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	< 12	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 1.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	28.0	MPa	ISO 527-2
Flexural Modulus	3500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	> 5.2	kJ/m <sup>2</sup>	ISO 179/B
Notched Izod Impact Strength	> 3.0	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 100	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate <sup>1</sup>	< 100	mm/min	ISO 3795
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 90.0	°C	
Rear Temperature	195 to 280	°C	
Middle Temperature	195 to 280	°C	
Front Temperature	195 to 280	°C	
Mold Temperature	20.0 to 70.0	°C	
NOTE			
1.	FMVSS 302		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT