

# ELASTOSIL® 7000 N

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, RTV-1

Sealants, Elastic, Construction

| General Information           |               |                   |             |
|-------------------------------|---------------|-------------------|-------------|
| Uncured Properties            | Nominal Value | Unit              | Test Method |
| Density                       | 1.02          | g/cm <sup>3</sup> | ISO 1183    |
| Consistency                   | non-sag       |                   | ISO 7390    |
| Cured Properties              | Nominal Value | Unit              | Test Method |
| Tensile Modulus (100% Secant) | 0.380         | MPa               | ISO 8339    |
| Tensile Strength              | 0.700         | MPa               | ISO 8339    |
| Tear Strength                 | 4.60          | kN/m              | ISO 34      |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

