

Nypol® PA A3 T30 NTLA010 NR426

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 with 30% mineral reinforced. Good set of thermal properties, electrical and mechanical. Ideal for injection molding.

General Information				
Filler / Reinforcement		Mineral,30% Filler by Weight		
Features		Good Electrical Properties		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		>PA 6.6 MD30<		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.34 to 1.36	--	g/cm ³	ASTM D792
Molding Shrinkage - Across Flow (2.00 mm)	0.20	--	%	ASTM D955
Water Absorption				ASTM D570
24 hr	1.2	--	%	
Saturation	7.5	--	%	
Ash Content	28 to 32	--	%	ASTM D2584
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	85.0	55.0	MPa	ASTM D638
Tensile Elongation (Break)	6.0	8.0	%	ASTM D638
Flexural Modulus	6000	2600	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ASTM D256
-30°C	11	9.0	kJ/m ²	
23°C	18	32	kJ/m ²	
Unnotched Izod Impact (Area)				ASTM D256
-30°C	10.0	8.00	kJ/m ²	
23°C	15.0	31.0	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	240	--	°C	
1.8 MPa, Unannealed	209	--	°C	
Peak Melting Temperature	250 to 265	--	°C	ASTM D2117
Injection	Dry	Unit		
Drying Temperature	80.0	°C		
Drying Time	4.0	hr		

Suggested Max Moisture	0.20	%
Processing (Melt) Temp	250 to 275	°C
Mold Temperature	60.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

