

Vipel® F282-ZZZ-00

Polyester Alloy

AOC, L.L.C.

Message:

Vipel® Corrosion Resistant Bisphenol A, Fumarate Based Polyester Resin

AOC's Vipel® F282 series resins are high molecular weight bisphenol A fumarate unsaturated polyester resins. Vipel® F282 series has an excellent shelf life and is ideal for filament winding and spray-up applications. One unique version is Vipel F282-ZZZ-00 which is the powdered alkyd product is an unique version that can be shipped abroad and blended locally with styrene or other monomers.

Corrosion resistance

Vipel® F282 is designed to make parts for a broad range of chemical environments such as acidic, bleach, hydrogen peroxide, oxidizing media, and caustic. Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC.

Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up, filament winding, etc.

It is the fabricator's responsibility to also be sure that the final composite is well cured. All composites used for FDA applications should be post cured at 180°F/82°C for at least 4 hours. After post curing , laminate should be washed with soap and water and then rinsed.

General Information			
Features	Acid Resistant		
	Food Contact Acceptable		
	Good Chemical Resistance		
	Good Corrosion Resistance		
	High Molecular Weight		
	Oxidation Resistant		
Uses	Coating Applications		
	Filaments		
Agency Ratings	FDA Unspecified Rating		
Forms	Liquid		
Processing Method	Filament Winding		
	Hand Lay-up		
	Spraying		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3030	MPa	ASTM D638
Tensile Strength	70.3	MPa	ASTM D638
Tensile Elongation (Break)	2.6	%	ASTM D638
Flexural Modulus	3030	MPa	ASTM D790
Flexural Strength	119	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	124	°C	ASTM D648
Thermoset	Nominal Value	Unit	

Post Cure Time (82°C)	4.0	hr
-----------------------	-----	----

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

