

Tool-A-Thane UT-505

Polyurethane

Urethane Tooling & Engineering Corp

Message:

Hardness 55 Shore A

Lowest loadbearing capacity

Not for forming applications.

General Information			
Uses	Molds/Dies/Tools		
Physical	Nominal Value	Unit	
Specific Gravity	1.22	g/cm ³	
Molding Shrinkage - Flow	1.5	%	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	55		
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction ¹ (vs. Steel - Dynamic)	> 0.80		
Abrasion Resistance - NBS Index	< 50.0		
Graves Tear	42.0	kN/m	
Penetration Depth - Recommended for optimum life	40	%	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
100% Strain	2.17	MPa	
300% Strain	5.31	MPa	
Tensile Strength	31.7	MPa	
Tensile Elongation (Break)	440	%	
Tear Strength (Split)	5.3	kN/m	ASTM D470
Thermal	Nominal Value	Unit	
Brittleness Temperature	-67.8	°C	
NOTE			
1.	at 20 lbs load at 52 fpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

