McCann PP M40CCPP10

Polypropylene Copolymer

McCann Plastics Inc.

Message:

McCann PP M40CCPP10 is a Polypropylene Copolymer (PP Copolymer) product filled with 40% calcium carbonate. It is available in North America. Applications of McCann PP M40CCPP10 include household applications, appliances, consumer goods and furniture.

Characteristics include:

Flame Rated Copolymer Good Stiffness Good UV Resistance

Impact Resistant

General Information					
Filler / Reinforcement	Calcium Carbonate,40% Filler by Weight				
Additive	UV Stabilizer				
Features	Copolymer				
	General Purpose				
	Good Flow				
	Good Impact Resistance				
	Good Stiffness				
	Good UV Resistance				
Uses	Appliances				
	Furniture				
	General Purpose				
	Household Goods				
	Lawn and Garden Equipment				
	Toys				
Appearance	Black				
	Colors Available				
	Natural Color				
Forms	Pellets				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.22	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR)	10	g/10 min	ASTM D1238		
Molding Shrinkage - Flow	1.2 to 2.0	%	ASTM D955		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	82		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		

Tensile Strength	18.6	MPa	ASTM D638
Tensile Elongation (Yield)	41	%	ASTM D638
Flexural Modulus - Tangent	1450	MPa	ASTM D790
Flexural Strength	32.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Gardner Impact	18.1	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	79.4	°C	
1.8 MPa, Unannealed	43.9	°C	
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

