

# Dutral® TER 4437

Ethylene Propylene Diene Terpolymer

Versalis S.p.A.

## Message:

Dutral ® TER 4437 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.

A non-staining antioxidant is added during the production process.

### Key Features

Dutral® elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral® TER 4437 is a very high molecular weight terpolymer of medium diene content, extended with 40% paraffinic oil.

It is characterized by high loading capacity, good dimensional stability, easier dispersion of ingredients during mixing and enhanced low temperature elasticity compared with Dutral ® TER 4436.

### Main Applications

Automotive, mechanical goods, appliances, TPV.

General Information		
Additive	Antioxidant	
Features	Antioxidant	
	Dispersible	
	Good Chemical Resistance	
	Good Dimensional Stability	
	Good Weather Resistance	
	High Elasticity	
	High Heat Resistance	
	Low Temperature Resistant	
	Terpolymer	
	Ultra High Molecular Weight	
Uses	Appliances	
	Automotive Applications	
	Compounding	
Forms	Bale	
Physical	Nominal Value	Unit
Mooney Viscosity (ML 1+4, 125°C)	57	MU
Ethylidene Norbornene (ENB) Content	4.5	wt%
Oil Type (Paraffinic Oil)	40.0	phr
Ash Content	< 0.3	wt%
Propylene Content	32.0	wt%
Volatiles	< 0.5	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT