

Unigel PS U8884

High Impact Polystyrene

Unigel Plásticos

Message:

Excellent performance in extrusion and thermoforming behaviour.
Good mechanical properties.
High performance in GPPS blends for general use sheet extrusion.
Approved for food contact

General Information	
Features	Food Contact Acceptable
Uses	Blending
	Sheet
Agency Ratings	FDA 21 CFR 177.1640
Processing Method	Extrusion
	Sheet Extrusion
	Thermoforming

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.8	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	0.070	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ASTM D638
Tensile Strength (Yield)	19.0	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.50 mm)	110	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.30 mm)	85.0	°C	ASTM D648
Vicat Softening Temperature	90.0	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

NOTE	
1.	Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

