

Makrolon® SF800 Z MAS148

Polycarbonate

Covestro - Polycarbonates

Message:

MVR (300 °C/1.2 kg) 9.0 cm³/10 min; structural foam; 5 % glass fiber reinforced; milled fiber; flame retardant; medium viscosity; easy release; injection molding; available in natural (opaque) and opaque colors; in combination with an appropriate blowing agent for the production of structural foam moldings

General Information			
UL YellowCard	E41613-100037155		
Filler / Reinforcement	Milled Glass Fiber,5.0% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Mold Release		
	Medium Viscosity		
Uses	Structural Foam		
RoHS Compliance	RoHS Compliant		
Appearance	Colors Available		
	Natural Color		
	Opaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.23	g/cm ³	ISO 1183
Apparent Density ¹	0.65	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.50	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 2.00 mm	0.55	%	
Flow : 2.00 mm	0.70	%	
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness			ISO 2039-1
--	120	MPa	
6.00 mm ³	50.0	MPa	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			

23°C	2700	MPa	ISO 527-2/1
23°C, 6.00 mm ⁴	1700	MPa	ISO 527-2/25
Tensile Stress			ISO 527-2/5
Yield, 23°C	60.0	MPa	
Break, 23°C, 6.00 mm ⁵	30.0	MPa	
Break, 23°C	50.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	4.8	%	
Break, 23°C, 6.00 mm ⁶	6.0	%	
Break, 23°C	55	%	
Flexural Modulus ⁷			ISO 178
23°C, 6.00 mm ⁸	1700	MPa	
23°C	2700	MPa	
Flexural Stress ⁹			ISO 178
3.5% Strain, 23°C	75.0	MPa	
3.5% Strain, 23°C, 6.00 mm ¹⁰	50.0	MPa	
23°C	90.0	MPa	
23°C, 6.00 mm ¹¹	50.0	MPa	
Flexural Strain at Flexural Strength			ISO 178
23°C ¹²	6.2	%	
23°C, 6.00 mm ¹³	5.0	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁴ (23°C, Complete Break)	20	kJ/m ²	ISO 7391
Charpy Unnotched Impact Strength			ISO 179/1eU
-60°C, Complete Break	170	kJ/m ²	
-30°C, Complete Break	210	kJ/m ²	
-20°C, Complete Break ¹⁵	50	kJ/m ²	
23°C, Complete Break	220	kJ/m ²	
23°C, Complete Break ¹⁶	50	kJ/m ²	
Notched Izod Impact Strength ¹⁷ (23°C, Complete Break)	20	kJ/m ²	ISO 7391
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	30.0	J	
23°C	35.0	J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-30°C	5100	N	
23°C	4400	N	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	138	°C	ISO 75-2/B
0.45 MPa, Unannealed, 6.00 mm Span ¹⁸	131	°C	ISO 75-2/B

1.8 MPa, Unannealed	128	°C	ISO 75-2/A
1.8 MPa, Unannealed, 6.00 mm ¹⁹	123	°C	ISO 75-2/A
Vicat Softening Temperature			ISO 306/B50
-- ²⁰	132	°C	
--	142	°C	
Ball Pressure Test (136°C)	Pass		IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 23 to 55°C	5.5E-5	cm/cm/°C	
Transverse : 23 to 55°C	6.5E-5	cm/cm/°C	
Thermal Conductivity ²¹ (23°C)	0.22	W/m/K	ISO 8302
RTI Elec (3.00 mm)	80.0	°C	UL 746
RTI Imp (3.00 mm)	80.0	°C	UL 746
RTI Str (3.00 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			IEC 60093
--	1.0E+16	ohms	
6.00 mm ²²	1.0E+16	ohms	
Volume Resistivity ²³ (23°C)	1.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
23°C, 1.00 mm	32	kV/mm	
23°C, 6.00 mm ²⁴	> 8.0	kV/mm	
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.10		
23°C, 1 MHz	3.00		
Dissipation Factor			IEC 60250
23°C, 100 Hz	8.0E-4		
23°C, 1 MHz	9.0E-3		
Comparative Tracking Index			IEC 60112
Solution A	200	V	
Solution B	125	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm, GY	V-0		
	V-0		
5.00 mm, GY ²⁵	5VA		
5.00 mm, GY	5VA		
Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	850	°C	
1.50 mm	960	°C	
3.00 mm	960	°C	

4.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.800 mm	900	°C	
1.50 mm	900	°C	
3.00 mm	900	°C	
Oxygen Index ²⁶	32	%	ISO 4589-2
NOTE			
1.	Pellets		
2.	60x60x2 mm, 500 bar		
3.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
4.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
5.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
6.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
7.	2.0 mm/min		
8.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
9.	2.0 mm/min		
10.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
11.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
12.	2 mm/min		
13.	2 mm/min, Foamed; density in the foamed state: 900 to 1000 kg/m ³		
14.	Based on ISO 179-1eA, 3 mm		
15.	Foamed 6.0 mm; density in the foamed state: 900 to 1000 kg/m ³		
16.	Foamed 6.0 mm; density in the foamed state: 900 to 1000 kg/m ³		
17.	Based on ISO 180-A, 3 mm		
18.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
19.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
20.	6.0 mm, Foamed; density in the foamed state: 900 to 1000 kg/m ³		
21.	Cross-flow		
22.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
23.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		
24.	Foamed; density in the foamed state: 900 to 1000 kg/m ³		

25.	Foamed; density in the foamed state: 900 to 1000 kg/m ³
26.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

