

DuraGrip® DGR 6160BK

Thermoplastic Elastomer

Advanced Polymer Alloys

Message:

DuraGrip® 6160BK is designed to be a special purpose Melt Processible Elastomer (MPE) that is easy to use in injection molding and extrusion processes. DGR 6160BK has an excellent soft touch feel and will Bond to Nylon, ABS, PC, PC/ABS. DuraGrip® 6100 series is hygroscopic and requires drying prior to use.

General Information			
Features	Good adhesion		
Agency Ratings	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 1.59mm	1.6	%	ASTM D955
Flow: 3.18mm	1.5	%	ASTM D955
Transverse flow: 1.59mm	0.0	%	ASTM D955
Transverse flow: 3.18mm	0.50	%	ASTM D955
Vertical flow direction: 1.59mm	0.0	%	ISO 294-4
Flow direction: 1.59mm	1.6	%	ISO 294-4
Vertical flow direction: 3.18mm	0.50	%	ISO 294-4
Flow direction: 3.18mm	1.5	%	ISO 294-4

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	58		ASTM D2240, ISO 868

Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1.0E 6g, CS-17 wheel)	189	mg	ASTM D1044

Elastomers	Nominal Value	Unit	Test Method
Tensile Set (100% Strain)	4	%	ASTM D412
Tensile Stress			
100% strain	2.21	MPa	ASTM D412
100% strain, 23°C	2.21	MPa	ISO 37
Tensile Strength (Yield, 23°C)	6.62	MPa	ASTM D412, ISO 37
Tensile Elongation			
Fracture	350	%	ASTM D412
Fracture, 23°C	350	%	ISO 37

Tear Strength ¹ (24°C)	29.4	kN/m	ASTM D624
Compression Set			ASTM D395B, ISO 815
24°C, 22 hr	21	%	ASTM D395B, ISO 815
70°C, 22 hr	82	%	ASTM D395B, ISO 815
100°C, 22 hr	91	%	ASTM D395B, ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air			
70°C, 168 hr	11	%	ASTM D573, ISO 188
100% strain, 70°C, 168 hr	2.0	%	ASTM D573
100°C, 168 hr	40	%	ASTM D573, ISO 188
100% strain, 100°C, 168 hr	-5.0	%	ASTM D573
100% strain 70°C, 168 hr	2.0	%	ISO 188
100% strain 100°C, 168 hr	-5.0	%	ISO 188
Change in Ultimate Elongation in Air			
70°C, 168 hr	4.0	%	ASTM D573
100°C, 168 hr	18	%	ASTM D573
Change in Tensile Strain at Break			
70°C, 168 hr	4.0	%	ISO 1817
100°C, 168 hr	18	%	ISO 1817
Change in Volume			
24°C, 168 hr, in reference fuel B	52	%	ASTM D471
70°C, 168 hr, ASTM Standard Oil (No. 1)	12	%	ASTM D471
70°C, 168 hr, in IRM 903 oil	74	%	ASTM D471
70°C, 168 hr, in water	2.0	%	ASTM D471, ISO 1817
24°C, 168 hr, in reference fuel B	52	%	ISO 1817
70°C, 168 hr, in ASTM #1 oil	12	%	ISO 1817
70°C, 168 hr, in IRM 903 oil	74	%	ISO 1817
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-65.0	°C	ASTM D746, ISO 812
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (190°C, 300 sec ⁻¹)	354	Pa · s	ASTM D3835
Additional Information			
The value listed as Density -Specific Gravity, ASTM D792, was tested in accordance with ASTM D471. The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.			
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	25	%	
Rear Temperature	204 - 221	°C	
Middle Temperature	216 - 227	°C	
Front Temperature	227 - 238	°C	
Nozzle Temperature	227 - 249	°C	

Processing (Melt) Temp	227 - 254	°C
Mold Temperature	43.3 - 54.4	°C
Injection Pressure	2.76 - 5.52	MPa
Screw Speed	50 - 150	rpm

Injection instructions

DuraGrip® is not hygroscopic, under normal conditions does not require drying. Dry in a desiccant dryer if porosity is observed.Injection Speed: 1 to 3 in³/secInjection Time (1st Stage/Boost): 0.5 to 4 secSecond Stage Pressure: 300 to 500 psiSecond Stage Time: 3 to 10 secCooling Time: 10 to 25 secBack Pressure: 25 to 75 %

NOTE

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT