

# Nylene® NX3055I

Polyamide 6  
Custom Resins Group

Message:

High-viscosity nucleated extrusion grade, suitable for film co-extrusion, cast and blown film  
Excellent melt stability and strength, faster set-up for increased line speeds  
Superior grease resistance, toughness, resistance to abrasion, and does not absorb food odors

General Information			
Additive	Nucleating Agent		
Features	Good Abrasion Resistance		
	Good Strength		
	Good Toughness		
	Grease Resistant		
	High Melt Stability		
	High Viscosity		
	Low Odor Transfer		
	Nucleated		
Uses	Cast Film		
	Film		
Agency Ratings	FDA Unspecified Rating		
	NSF Unspecified Rating		
Processing Method	Blown Film		
	Cast Film		
	Coextrusion		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Films	Nominal Value	Unit	Test Method
Secant Modulus - MD	652	MPa	ASTM D882
Tensile Strength - MD (Break)	59.6	MPa	ASTM D882
Tensile Elongation - MD (Yield)	290	%	ASTM D882
Elmendorf Tear Strength (23°C)	21.6	kN/m	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	216	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

