

EverGlide® SG3208T

Polyetheretherketone

Polymer Dynamix

Message:

Lubricated PEEK

Features:

Excellent Chemical Resistance

Low Temperature Flexibility

Excellent Processability

Applications:

Automotive

Aerospace

Industrial

General Information	
Additive	Lubricant
Features	Good Chemical Resistance
	Good Processability
	Low Temperature Flexibility
	Lubricated
Uses	Aerospace Applications
	Automotive Applications
	Industrial Applications

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	51.7	MPa	
Break	37.9	MPa	
Tensile Elongation			ASTM D638
Yield	9.0 to 10	%	
Break	> 75	%	
Flexural Modulus	2620	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	64	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

