

NORDEL™ IP 3430

Hydrocarbon Rubber

The Dow Chemical Company

Message:

NORDEL™IP 3430 hydrocarbon rubber is an amorphous ethylene-propylene-diene terpolymer (EPDM) with extremely low diene content, suitable for peroxide cured articles. NORDEL IP 3430 can also be blended with butyl rubber to improve its processing performance and vulcanization performance. It is applied to tire inner tube materials for automobiles and bicycles.

Main features:

amorphous

very low diene content

Low molecular weight

Heat stability and UV stability

Comply with the following regulations

Requirements of the FDA Regulation 21 CFR 177.2600,

Requirements of the FDA Regulation 21 CFR 177.1520 (see Note 1),

The requirements of the FDA Regulation 21 CFR 175.105 (see Note 2),

Requirements of the FDA Regulation 21 CFR 177.1210.

Please check the regulations for complete details.

Application field:

Blend with butyl rubber as a blending component for tire inner tubes

Peroxide cured molded parts

remarks:

(1) can be used to contact all types of food, except oil emulsion water, high-fat or low-fat food, low-humidity fat and oil food.

(2) Adhesive only.

General Information			
Agency Ratings	FDA 21 CFR 175.105		
	FDA 21 CFR 177.1210		
	FDA 21 CFR 177.1520		
	FDA 21 CFR 177.2600		
Forms	bag		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860	g/cm ³	ASTM D297
Mooney Viscosity (ML 1+4, 125°C)	27	MU	ASTM D1646
Ethylene Content	42.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	0.8	wt%	ASTM D6047
Propylene content	57.0	wt%	ASTM D3900
Residual conversion metal		ppm	Internal method
Molecular Weight Distribution	Narrow		Internal method
Ash Content		wt%	ASTM D5667
Volatile Matter		wt%	Internal method
Additional Information			

存放和处理:暴露在人造光或自然光中可能影响 EPDM 产品的质量.此产品应采用其原始包装并存放在室内,同时避免阳光直射.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT