

SABIC® PP 5704N

Polypropylene Homopolymer

SABIC Americas, Inc.

Message:

Provisional - PP Homopolymer for Injection Molding

PP 5704N is a controlled rheology PP grade of narrow molecular weight distribution with antistatic and nucleated agents. It is suitable for producing injection molded applications and gives consistent processability, good flow properties for excellent part filling and good gloss at the products.

Typical Applications

PP 5704N can be used for household articles, toys, thin wall food packaging items with good dimensional stability.

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Controlled Rheology		
	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Flow		
	Good Processability		
	High Gloss		
	Homopolymer		
	Narrow Molecular Weight Distribution		
	Nucleated		
Uses	Food Packaging		
	Household Goods		
	Toys		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.905	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2 to 2.5	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	35.0	MPa	ASTM D638

Tensile Elongation (Yield, Injection Molded)	10	%	ASTM D638
Flexural Modulus - 1% Secant (Injection Molded)	1500	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 ²
Injection	Nominal Value	Unit	
Rear Temperature	200 to 225	°C	
Middle Temperature	200 to 225	°C	
Front Temperature	200 to 225	°C	
Mold Temperature	15.0 to 40.0	°C	
NOTE			
1.	23°C		
2.	Rate B (120°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

