MARPOL® F-M

Expanded Polystyrene

Marco Polo International, Inc.

Message:

APPLICATIONS: Insulation board, large parts and medium parts packaging

General Information		
Features	Can foam	
Uses	Packaging	
	Foamed insulation board	

Physical	Nominal Value	Unit
Specific Gravity	1.03	g/cm³
Humidity		%
Pentane Content	6.0	%
Polystyrene Content	> 93	%
Bead Size	0.900 - 1.80	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

