

APEX® 4111

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX®4111 is a flexible polyvinyl chloride material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

APEX®The main features of the 4111 are:

flame retardant/rated flame

ROHS certification

Typical application areas include:

Wire and cable

engineering/industrial accessories

Electrical/electronic applications

General Information			
UL YellowCard	E54709-245331	E142591-543084	
Uses	Plug Wire and cable applications Washer Connector Fatigue elimination supplies		
Wire Types	Molded member		
Agency Ratings	UL QMFZ2 .E54709		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.0 - 1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	18.8	MPa	ASTM D638
Tensile Elongation (Break)	280	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	ASTM D794
Brittleness Temperature	-10.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI) (3.00 mm)	PLC 0		UL 746
High Amp Arc Ignition (HAI) (3.00 mm)	PLC 1		UL 746

Hot-wire Ignition (HWI) (3.00 mm)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-0		UL 94
Oxygen Index	31	%	ASTM D2863
Additional Information			
温度额定值:105°C认证部件,CSA C22.2 No. 0.6,CSA 可燃性等级:0.6V-2 @ 0.81 毫米			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	193	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

