

Hifax TYC 258P C1V301

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hifax TYC 258P C1V301 is a 30% talc filled PP copolymer, with low shrinkage, high flowability, good impact/stiffness balance and high UV resistance. The product is available in different color matched, pellet form. This grade is delivered in C1V301 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

General Information			
Filler / Reinforcement	Talc filler, 30% filler by weight		
Features	Rigid, good		
	Impact resistance, good		
	Good UV resistance		
	High liquidity		
	Low shrinkage		
Uses	Application in Automobile Field		
	Car exterior decoration		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.14	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	18.0	MPa	ISO 527-2
Tensile Strain (Break)	50	%	ISO 527-2
Flexural Modulus ¹ (23°C)	1900	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	2.5	kJ/m ²	ISO 179/1eA
23°C	25	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	100	°C	ISO 75-2/B
Vicat Softening Temperature	115	°C	ISO 306/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

