

ResMart Ultra HoPP 12

Polypropylene Homopolymer

ResMart

Message:

Prime Homopolymer Polypropylene barefoot that provides a good balance of properties with good melt flow.

General Information			
Features	Good Flow		
	Homopolymer		
Agency Ratings	FDA Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	38.6	MPa	ASTM D638
Flexural Modulus	1520	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	79.4	°C	
Drying Time - Desiccant Dryer	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

