

Durethan® BG 30 X 000000

Polyamide 6

LANXESS Corporation

Message:

PA 6, 30 % glass fibers/glass spheres, injection molding, low tendency to warp

General Information				
UL YellowCard		E245249-473570		
Filler / Reinforcement		Glass Beads \Glass Fiber, 30% Filler by Weight		
Features		Low warpage		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.35	--	g/cm ³	ASTM D792
23°C	1.35	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.77	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.16	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.48	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.12	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	7.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.2	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	185	75.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	6200	3500	MPa	ASTM D638
23°C	6300	3100	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	125	64.8	MPa	ASTM D638
Fracture, 23°C	125	65.0	MPa	ISO 527-2/5
Tensile Elongation				
Fracture, 23°C	4.0	9.0	%	ASTM D638
Fracture, 23°C	4.0	10	%	ISO 527-2/5

Tensile Creep Modulus				ISO 899-1
1 hr	--	2400	MPa	ISO 899-1
1000 hr	--	2000	MPa	ISO 899-1
Flexural Modulus				
23°C	5500	2800	MPa	ASTM D790
23°C ⁶	5800	2800	MPa	ISO 178/A
Flexural Strength				
23°C	195	110	MPa	ASTM D790
3.5% strain, 23°C	170	80.0	MPa	ISO 178/A
23°C ⁷	185	100	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁸ (23°C)	5.0	8.0	%	ISO 178/A
Burning Behavior ⁹	passed	--		ISO 3795
ISO Shortname	PA 6, GR, 14-060, (GB+GF) 30 --			ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	45	kJ/m ²	ISO 179/1eU
23°C	45	75	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
-40°C, 3.18 mm	48	48	J/m	ASTM D256
23°C, 3.18 mm	59	140	J/m	ASTM D256
-40°C	< 10	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	30	40	kJ/m ²	ISO 180/1U
23°C	35	60	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	1.70	--	J	ISO 6603-2
23°C	2.00	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	690	--	N	ISO 6603-2
23°C	700	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method

Deflection Temperature Under Load				
0.45 MPa, unannealed, 39.9mm	200	--	°C	ASTM D648
0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	190	--	°C	ISO 75-2/A
1.8 MPa, annealing, 3.99mm	180	--	°C	ASTM D648
Vicat Softening Temperature	> 200	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ¹⁰	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	3.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
RTI Elec (1.50 mm)	120	--	°C	UL 746
RTI Imp (1.50 mm)	90.0	--	°C	UL 746
RTI (1.50 mm)	125	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14 - 1.0E+16	1.0E+12 - 1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+11 - 1.0E+12	ohms·cm	IEC 60093
Dielectric Strength				IEC 60243-1
23°C, 1.00 mm	36	30	kV/mm	IEC 60243-1
23°C, 3.00 mm	35	35	kV/mm	IEC 60243-1
Dielectric Constant				IEC 60250
23°C, 50 Hz ¹¹	4.50	10.0		IEC 60250
23°C, 1 MHz ¹²	4.00	5.00		IEC 60250
23°C, 100 Hz	4.50	16.0		IEC 60250
23°C, 1 MHz	4.00	4.80		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.015	0.20		IEC 60250
23°C, 100 Hz	0.013	0.31		IEC 60250
	0.020	0.060		
23°C, 1 MHz	0.018	0.10		IEC 60250
Arc Resistance ¹³	--	110	sec	ASTM D495
Comparative Tracking Index				
Solution a	400	--	V	IEC 60112
--	--	450	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.50 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94

3.00 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹⁴	23	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	1.0 mm/min
6.	2.0 mm/min
7.	2.0 mm/min
8.	2 mm/min
9.	US-FMVSS302
10.	10°C/min
11.	Tinfoil Electrodes
12.	Tinfoil Electrodes
13.	Tungsten Electrodes
14.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT