

4PROP® 9C22430

Polypropylene Copolymer
4Plas

Message:

4PROP 9C22430 is a MFI 15 30% Chemically Coupled Glass Fibre Copolymer Polypropylene

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Copolymer		
	Chemical coupling		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	5500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	15	kJ/m ²	ISO 180/1A
23°C	25	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	135	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	20.0 - 50.0	°C	
Injection Rate	Moderate		
Holding Pressure	40.0 - 80.0	MPa	
Screw Speed	200	rpm	
Injection instructions			
Feed Throat Temperature: 20 - 60 °CBack Pressure: Low			

NOTE

1. 10 K/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

